

### PINK BLOCKER 2C – COLOR + CLEAR – Code:230-xxxxxx

#### DESCRIPTION

PINK BLOCKER 2C is a special water based reactive product to “discolor” and “block” the pink and red effect on wood.

Afterwards the substrate can be finished with (reactive) stains, UV Oil, Ecofix, Oculito, Hardwaxoils, UN1CO, Wax.... Out of the Ciranova range.

#### APPLICATION

Conventional / Airmix spraying  
manual application

#### TECHNICAL DATA

Mixing ratio  
clear / stain 1/1  
Density mix +/- 1.00 KG/L  
Viscosity as water  
Solid Content depending component  
Cleaning: water  
Reaction time: minimum 6 hrs

#### CERTIFICATES

NA

#### PACKAGING

5 + 5LT  
25 + 25LT

#### USER INSTRUCTIONS

Prepare the wood according the rules of the art and remove the sanding dust carefully.

Mix the PINK BLOCKER CLEAR with the PINK BLOCKER STAIN 1/1.

After mixing, the liquid can only be used for a few weeks. During the application of the stain, stirr regularly.

- Stirr well before use.
  - **Spraying** : apply +/- 60g/m<sup>2</sup>, leveling with a brush.
- Or
- **Manual application** : apply the PINK BLOCKER 2C ca 60g/m<sup>2</sup> with a brush in the direction of the wood fiber. Leveling afterwards with a brush.

Depending on the redness of the wood you can adjust the recommended application quantity.

**For this reason it is always recommended to make a test first before starting production.**

After respecting the reaction time, it is recommended to apply 1 coat of Ecofix or Oculito to block the color before protecting with an oil or a lacquer.

#### REMARKS

- Only use stainless material. Clean immediately after use.
- After complete reaction time, smoothen the surface with a pad or sanding brush.

#### MAINTENANCE

NA

#### WAREHOUSING by “10 – 40 °C

12 months in well-closed and original packaging.



” All tests and application methods are done with the above-mentioned Debal Coatings components. We are not responsible for application with other materials, unless written agreement from Debal Coatings.”  
DATE : 01/2019